

Truly

Water absorption moisture permeation oil repellency and Soil release finish durability verification test

1. Summary

A verification test was performed to examine the durability of its stain release on Satin (P100%) and Double-Pique (P100%) . Truly (No. 2) showed great results and excellent durability even after 30 washes.

2. Test Materials: ①Satin (PE100%) ②Double-Pique (PE100%)

3. Test Results

		1	2
		Normal Fabric Softner	Truly
Stain release (grade) Diamond Paste	① Initial state	3	4-5
	HL-10 (air-dried)	—	4-5
	HL-20 (air-dried)	—	4-5
	HL-30 (air-dried)	—	4-5
	② Initial state	2	5
	HL-10 (air-dried)	—	5
	HL-20 (air-dried)	—	5
	HL-30 (air-dried)	—	5

Stain Release test (Company act) : A drop of stain material (Diamond Paste) is placed on the testing cloth covered by a load of 500g for one minute. After removing it, it is left on room temperature for one hour and washed once with method Act103. A visual judgment was made after it was dried.

Washing : JIS L-207 Act 103

